



US006990736B2

(12) **United States Patent**
West

(10) **Patent No.:** **US 6,990,736 B2**
(45) **Date of Patent:** **Jan. 31, 2006**

(54) **METHODS FOR PREPARING JEWELRY ARTICLES COMPRISING SINTERED TUNGSTEN CARBIDE**

1,327,606 A *	1/1920	Bacharach	63/15.2
1,431,652 A *	10/1922	Grossman	29/8
1,537,068 A *	5/1925	Croselmire	63/15
1,597,589 A	8/1926	Ferrari	132/73.5
1,654,335 A	12/1927	Lindroth	
1,689,124 A	10/1928	Fitzgerald	

(76) Inventor: **Trent West**, 41 Hangar Way, Watsonville, CA (US) 95076

(*) Notice: Subject to any disclaimer, the term of this patent is extended or adjusted under 35 U.S.C. 154(b) by 37 days.

(Continued)

FOREIGN PATENT DOCUMENTS

AU 208883 8/1956

(Continued)

OTHER PUBLICATIONS

Progressive Jewelers.com Webpage [Available] <http://www.progressivejewelers.com/tungsteninlays.htm>; ©2003.

(Continued)

(21) Appl. No.: **10/410,655**

(22) Filed: **Apr. 8, 2003**

(65) **Prior Publication Data**

US 2004/0025347 A1 Feb. 12, 2004

Related U.S. Application Data

(60) Division of application No. 09/571,583, filed on May 15, 2000, now Pat. No. 6,553,667, which is a continuation-in-part of application No. 09/149,796, filed on Sep. 8, 1998, now Pat. No. 6,062,045.

(60) Provisional application No. 60/058,136, filed on Sep. 8, 1997.

(51) **Int. Cl.**

A44C 27/00 (2006.01)
B21D 39/00 (2006.01)

(52) **U.S. Cl.** **29/896.412**; 29/508; 29/8

(58) **Field of Classification Search** 29/896.4, 29/896.41, 896.411, 896.412, 508, 8; 63/15.2, 63/15, 15.7, 15.8, 15.4; D11/38
See application file for complete search history.

(56) **References Cited**

U.S. PATENT DOCUMENTS

D33,674 S * 12/1900 Bliss D11/4
1,192,983 A * 8/1916 Bruderer 29/896.412


Primary Examiner—Marc Jimenez

(74) *Attorney, Agent, or Firm*—Winston & Strawn LLP

(57) **ABSTRACT**

System, apparatus, and method for making composite articles including jewelry rings. Jewelry items such as finger rings, bracelets, earrings, body jewelry, and the like, are examples of such articles. Medical, dental, and industrial devices or components are other examples. Wear resistant jewelry apparatus and method of making same wherein articles of jewelry are made from sinterable metal and/or ceramic powder materials compressed into a predetermined configuration and then sintered to form a blank from which a jewelry item may be made and to which softer precious metals, stones, crystals or other materials suitable for use in jewelry may be affixed. Such items of jewelry may have multiple facets and can be fabricated using various disclosed techniques and various combinations of materials. Method of manufacturing an article including jewelry rings.

24 Claims, 12 Drawing Sheets



US 6,990,736 B2

Page 2

U.S. PATENT DOCUMENTS

1,863,618 A	6/1932	Brogan	29/10
2,016,679 A	10/1935	Mayer	63/15
2,027,060 A	1/1936	Niven et al.	63/15
2,050,253 A *	8/1936	Bager	63/15
2,128,644 A *	8/1938	Gittler	63/15
2,161,549 A	6/1939	Most	428/67
2,332,344 A *	10/1943	Roskin	63/15
2,450,762 A *	10/1948	Marshall	63/15.2
3,242,664 A	3/1966	Lederrey	368/281
3,409,416 A	11/1968	Yates	29/182.5
3,413,392 A	11/1968	Meadows	264/102
3,417,223 A	12/1968	Steigerwald	219/121
3,606,766 A	9/1971	Hill	63/15
3,669,695 A	6/1972	Iler et al.	106/43
3,712,079 A	1/1973	Eberle	63/15
3,719,479 A	3/1973	Flanagan	75/226
3,725,634 A	4/1973	Lane	219/121
3,776,706 A	12/1973	Daniels	29/182.5
3,837,163 A	9/1974	Fujimori	59/80
3,841,848 A	10/1974	Kasai et al.	428/564
3,901,717 A	8/1975	Revaz	106/42
4,090,284 A	5/1978	Kraft	29/159.3
4,281,235 A	7/1981	Peloquin	219/121
4,387,627 A	6/1983	Avezou	92/222
4,549,058 A	10/1985	DelMastro et al.	219/121
4,574,011 A *	3/1986	Bonjour et al.	75/241
4,740,935 A	4/1988	Gogniat	368/294
4,891,276 A	1/1990	Exner	428/670
5,003,678 A	4/1991	Oganesyan	29/10

5,431,028 A	7/1995	Lampert et al.	63/2
5,462,772 A	10/1995	Lemelson	427/554
5,678,428 A *	10/1997	Pasquetti	63/15.2
5,968,428 A	10/1999	Kuwabara	264/86
6,062,045 A	5/2000	West	63/15
D435,475 S *	12/2000	Canty	D11/26
6,260,383 B1	7/2001	Warren et al.	63/15
6,546,749 B1	4/2003	Canty	63/3
6,553,667 B1	4/2003	West	29/896.412
6,641,640 B1	11/2003	Hesse et al.	75/236

FOREIGN PATENT DOCUMENTS

GB	950127	2/1964
GB	2 210 249	6/1989
JP	56084375 A	7/1981
JP	59-076801	5/1984
JP	61-177351	8/1986
JP	64-008245	1/1989
JP	9268241	10/1997
WO	WO 99/12443	3/1999
WO	WO 02/21962	3/2002

OTHER PUBLICATIONS

Boccia® Titanium, The Boccia Titanium Jewelry Collection, Universal Watch Co., Inc., Framingham, MA 01712, Aug. 6, 2002.

Dictionary.Reference.com, definition of word “ring”.

* cited by examiner




FIG. 1




FIG. 2




FIG. 3




FIG. 4




FIG. 5




FIG.6




FIG. 7




FIG. 11




FIG. 8




FIG. 12




FIG. 9




FIG. 13




FIG. 10




FIG. 14




FIG. 15




FIG. 16




FIG. 17




FIG. 18




FIG. 19A




FIG. 19B

125
↘




FIG.20




FIG. 21




FIG. 22

285




FIG.23

**METHODS FOR PREPARING JEWELRY
ARTICLES COMPRISING SINTERED
TUNGSTEN CARBIDE**

**CROSS REFERENCE TO RELATED
APPLICATIONS**

This application is a divisional of and claims the benefit of priority to application Ser. No. 09/571,583, filed May 15, 2000, now U.S. Pat. No. 6,553,667, which is a continuation-in-part of and claims priority to application Ser. No. 09/149,796, filed Sep. 8, 1998, now U.S. Pat. No. 6,062,045, which itself claims the benefit of the priority date of the earlier filed U.S. Provisional Patent Application No. 60/058,136, filed Sep. 8, 1997, each of which is incorporated herein by reference thereto.

FIELD OF THE INVENTION

The present invention relates generally to an apparatus and method for manufacturing a composite article and to the article manufactured by that apparatus and method, and more particularly to an apparatus and method for manufacturing an article having a hard, wear-resistant component and a softer, more malleable component, such as articles made from "hard" metals and/or ceramic materials either alone or in combination with precious metals and jewels such that the hardened materials protect the softer precious metals and jewels from edge and detail wear down, including to jewelry items such as finger rings, bracelets, earrings, body jewelry, and the like, and medical or industrial devices or components.

BACKGROUND OF THE INVENTION

Jewelry has for centuries been made of soft materials such as gold, silver, platinum and other soft materials because such metals were malleable, and easily cast, forged, molded or otherwise formed. However, whereas such materials are relatively easy to form, shape and polish, they are equally subject to wear, scratching and other damage detracting from their longevity appearance and value, i.e., wearing down of edges to a smooth and rounded state.

More recently, science has produced other materials including tungsten, cemented carbide and high-tech ceramics that are much harder than the previously mentioned precious metals, and once formed, are virtually indestructible when used in a normal jewelry wearing environment. One problem with such materials is that because of their hardness, they are very difficult to shape, and once formed, require special machining and/or grinding tools to alter their configuration and appearance. Accordingly, with the exception of articulated watch bands or housings for certain timepieces, such materials have historically not been used for articles of jewelry of the types mentioned above. However, I have recently discovered that through the use of powder metallurgy and sintering processes, such materials can be manufactured and used to provide faceted designs that were not heretofore practiced. Furthermore, such materials can be used to enhance and protect precious metals and gemstones in this jewelry setting.

In the process of fabricating parts from powdered metals, the most important step is one involving the welding together of the metallic powder to form a solid which will yield the proper shape and the properties required of the finished part. Although a good weld cannot be made between metals at room temperature by pressure alone, when the

metal particles are relatively fine and plastic, a welding may occur that is satisfactory from the view point of handling, although little or no strength will be developed. Under pressure, at room temperature, metal powders that are plastic and relatively free from oxide films, may be compacted to form a solid of the desired shape having a strength (green strength) that allows the part to be handled. This result is often called cold-welding. The welding under pressure of the metal particles in order form a solid blank of the shape desired, requires the use of pressures varying from 5 to 100 tons-per-square inch. Relatively light loads are used for the molding of the solder and more plastic metals, while pressures approaching 100 tons per square inch are necessary when maximum density is needed and when pressing relatively hard and fine metal powders such as those mentioned above are used in accordance with the present invention.

Commercial pressing is done in a variety of presses which may be of the single mechanical punch-press type or the double—action type of machine that allows pressing from two directions by moving upper and lower punches synchronized by means of cams. These machines also incorporate moveable core rods which make it possible to mold parts having long cores, assist in obtaining proper die fills and help in the ejection of the pressed parts.

The molding of small parts at great speeds and at relatively low pressures can be accomplished using the mechanical press. For example, mechanical presses can produce parts at the rate of 300 to 30,000 parts per hour. A satisfactory press should meet certain definite requirements among which are the following: (1) sufficient pressure should be available without excessive deflection of press members; (2) the press must have sufficient depth of fill to make a piece of required heights dependent upon the ratio of loose powder to the compressed volume, this being referred to as the compression ration; (3) a press should be designed with an upper or lower punch for each pressing level required in the finished part, although this may be taken care of by a die design with a shoulder or a spring mounted die which eliminates an extra punch in the press; and (4) a press should be designed to produce the number of parts required. The punches are usually made from an alloy of tungsten carbide or punched steel that can be hardened by oil quenching.

Heating of the cold-welded metal powder is called the "sintering" operation. The function of heat applied to the cold-welded powder is similar to the function of heat during a pressure-welding operation of steel in that it allows more freedom for the atoms and crystals; and it gives them an opportunity to re-crystalize and remedy the cold deformation or distortion within the cold pressed part. The heating of any cold-worked or deformed metal will result in re-crystallization and grain growth of the crystals or grains within the metal. This action is the same one that allows one to anneal any cold work-hardened metal and also allows one to pressure-weld metals. Therefore, a cold-welded powder will re-crystalize upon heating, and upon further heating, the new crystals will grow, thus the crystal grains become larger and fewer.

The sintering temperatures employed for the welding together of cold-pressed powders vary with the compressive loads used, the type of powders, and the strength required of the finished part. Compacts of powders utilized in accordance with the present invention are typically sintered at temperatures ranging from about 1000° C. to in excess of 2000° C. for approximately 30 minutes. When a mixture of different powders is to be sintered after pressing and the individual metal powders in the compact have markedly

different melting points, the sintering temperatures used can be above the melting point of one of the component powders. The metal with a low melting point will thus become liquid; however, so long as the essential part or major metal powder is not molten, this practice may be employed. When the solid phase or powder is soluble in the liquid metal, a marked delusion of the solid metal through the liquid phase may occur which will develop a good union between the particles and result in a high density.

Most cold-pressed and metal ceramic powders shrink during the sintering operation. In general, factors influencing shrinkage include particle size, pressure used in cold-welding, sintering temperature and time employed during the centering operation. Powders that are hard to compress will cold-shrink less during sintering. It is possible to control the amount of shrinkage that occurs. By careful selection of the powder and determination of the correct pressure for cold-forming it is possible to sinter so as to get minimal volume change. The amount of shrinkage or volume change should be determined so as to allow for this change in the design of the dies used in the process of fabricating a given shape.

The most common type of furnace employed for the sintering of pressed powders is the continuous type. This type of furnace usually contains three zones. The first zone warms the pressed parts and the protective atmosphere used in the furnaces purges the work of any air or oxygen that may be carried into the furnace by the work or trays. This zone may be cooled by water jackets surrounding the work. The second zone heats the work to the proper sintering temperature. The third zone has a water jacket that allows for rapid cooling of the work; and the same protective atmosphere surrounds the work during the cooling cycle.

Protective atmospheres are essential to the successful sintering of pressed powders. The object of such an atmosphere is to protect the pressed powders from oxidation which could prevent the successfully welding together of the particles of metal powder. Also if a reducing protective atmosphere is employed, any oxidation that may be present on the powder particles will be removed and thus aide in the process of welding. A common atmosphere used for the protection and reduction of oxides is hydrogen. Water vapor should be removed from the hydrogen gas by activated alumina dryers or refrigerators before it enters the furnace.

Many of the same problems and limitations experienced in the jewelry industry also pertain to the medical, dental, industrial, and scientific fields where there is a need for articles having particular structural and/or metallurgical or compositional properties have been difficult to manufacture.

Therefore there remains a need for articles having properties that are best met using composite materials, and methods, apparatus, and systems for making such articles.

SUMMARY OF THE INVENTION

The invention includes system, apparatus, and method for making composite articles. Such system and method are particularly well adapted to make composite articles having a hard, wear-resistant component and a softer, more malleable component. One such article is an article made from "hard" metals and/or ceramic materials either alone or in combination with precious metals and jewels such that the hardened materials protect the softer precious metals and jewels from edge and detail wear down. Jewelry items such as finger rings, bracelets, earrings, body jewelry, and the like, are one particular example of such articles. Medical, dental, and industrial devices or components are other examples of such articles. Furthermore, while the manufac-

turing method or process is particularly well suited to articles having a wear resistant component and a softer wearable component, the inventive method is not limited to such hard and soft constituents.

In one aspect, the invention provides a method of manufacturing a composite article including a substrate comprising a first material and an inlay comprising a second material. The method includes the steps of preheating the substrate; contacting a depression in a surface of the substrate with the second material; heating the second material at a point contact with the substrate causing it to liquefy and flow into the depression; and moving the point of contact along the along the depression in the surface of the substrate while continuously feeding the second material and heating the second material at the point contact with the substrate to cause it to substantially fill the depression. The method may also optionally include generating the heat using an electron beam, applying a de-focused electron beam to the surface of the substrate to preheat the substrate, and applying a focused electron beam to the second material at the point contact with the substrate. Here, the process is advantageously carried out in a high-vacuum atmospheric environment.

The inventive method may be utilized with a cylindrical, spherical, or ring-shaped substrate having an outer surface and wherein the depression comprises a groove disposed circumferentially therein, and wherein the step of moving the point of contact along the depression in the surface of the substrate includes rotating the substrate to move the point of contact along the along the groove.

In another aspect, the invention provides a method of manufacturing a composite article including a cylindrical, spherical, annular, or ring-shaped substrate comprising a first material and a metal wire comprising a second material, where the method includes the steps of: joining ends of the metal wire to form a metal ring) or otherwise fabricating or machining to form a seamless metal ring or other article) having an inner diameter greater than an outer diameter of the ring-shaped substrate; placing the metal ring over a groove disposed circumferentially in an outer surface; placing the substrate with the metal ring thereon on a mandrel; positioning the mandrel in a collet in an opening of a collet-block, the collet comprising a tapered hollow cylinder having a plurality of tines capable of being deformed radially inward to squeeze the metal ring into the groove of the ring-shaped substrate, the collet tapering from a maximum outer diameter proximal to a top end of the collet to a minimum outer diameter distal from the top end, and the opening in the collet-block comprising a inner diameter that tapers from a maximum proximal to a top surface of the collet-block to a minimum distal from the top surface; and forcing the collet with the mandrel positioned therein into the opening; so that the metal ring is squeezed into the groove in the ring-shaped substrate to form the composite article.

The invention further includes an object or article formed or manufactured using any of the inventive systems, apparatus, and/or method.

It is therefore a principal objective of the present invention to provide novel items formed from a combination of different materials and a system and method for making such items.

BRIEF DESCRIPTION OF THE DRAWINGS

These and various other features and advantages of the present invention will be apparent upon reading of the

5

following detailed description in conjunction with the accompanying drawings, where:

FIG. 1 is a diagram schematically illustrating a press mold of a type used to make jewelry articles in accordance with the present invention;

FIG. 2 is a partially broken perspective view illustrating details of one form of a molded ring component in accordance with the present invention;

FIG. 3 is a perspective view illustrating one step in the preparation of a ring component in accordance with the present invention;

FIG. 4 is an illustration depicting a sintering step in accordance with the present invention;

FIG. 5 is a perspective view illustrating one method of combining a precious metal component with a hard metal and/or ceramic component in accordance with the present invention;

FIG. 6 is a flow chart illustrating steps followed to make jewelry in accordance with one embodiment of the present invention;

FIGS. 7-14 are partial cross-sections taken through various embodiments illustrating alternative forms of rings made in accordance with the present invention;

FIG. 15 illustrates a unitary multifaceted hard metal/ceramic ring; and

FIG. 16 depicts a precious metal ring having a hard metal/ceramic band embedded therein to provide a protective outer wear surface.

FIG. 17 is a schematic side view of an embodiment of an apparatus for forming an article according to the present invention;

FIG. 18 is a schematic side view of an embodiment of an indexer of the apparatus of FIG. 17;

FIGS. 19A and 19B are schematic side views of an embodiment of a mandrel for holding substrates in the apparatus of FIG. 17;

FIG. 20 is a flowchart of an embodiment of a process for manufacturing an article according to an embodiment of the present invention;

FIG. 21 is a schematic side view of another embodiment of an apparatus for forming an article according to the present invention;

FIG. 22 is a schematic side view of an embodiment of a mandrel for holding substrates in the apparatus of FIG. 21; and

FIG. 23 is a flowchart of an embodiment of another process for manufacturing an article according to an embodiment of the present invention.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

The invention includes system, apparatus, and method for making composite articles particularly to an apparatus and method for manufacturing an article having a hard, wear-resistant component and a softer, more malleable component. One such article is an article made from "hard" metals and/or ceramic materials either alone or in combination with precious metals and jewels such that the hardened materials protect the softer precious metals and jewels from edge and detail wear down. Jewelry items such as finger rings, bracelets, earrings, body jewelry, and the like, are one particular example of such articles. Medical, dental, and industrial devices or components are other examples of such articles. Furthermore, while the manufacturing method or process is particularly well suited to articles having a wear resistant component and a softer wearable component, the inventive

6

method is not limited to such hard and soft constituents. The broad applicability of the inventive articles and method for making such articles will become more apparent in light of the description and drawings provided herein.

Referring now to FIG. 1 of the drawing, a compressive mold is depicted at **10** including an annular cavity **12** generally illustrated and configured to receive a quantity of powdered hard metal or high tech ceramic material that can be compressed and formed into an oversized "green" ring blank by the application of compressive forces applied by a mating press member **14**. The mold **10** may be made in any configuration suitable for forming a particular annular or other shape; and the illustrated cavity is sized to as to produce an annular blank that, following shrinkage during subsequent processing, will have a predetermined size and configuration. Numerous types of powdered materials can be used in accordance with the present invention. One such powder includes the following constituents:

Nickel	2% to 10%
Cobalt	1% to 2%
Chromium or Chromium Carbide	0.5% to 3%
Tungsten or Tungsten Carbide	balance

Whereas in this example, Nickel and Cobalt are used as binder materials, other materials such as palodium, platinum, ruthenium, iridium and gold or alloys thereof, may also be used.

A ceramic composition might include:

ZIRCONIA (wt. %)

ZrO ₂ + HfO ₂	99%
SiO ₂	0.20%
TiO ₂	0.15%
Fe ₂ O ₃	0.02%
SO ₃	0.25%
LOI @ 1400°	0.30%

Whereas in this example, ZrO₂+HfO₂ is used as the matrix material, silicon nitrides, silicon carbides and other similar materials may be used. In addition, various casting agents may be included in the binding materials.

In FIG. 2 of the drawing, one configuration of a ring is illustrated at **20** and includes an annular external groove **22** formed in the outer surface thereof. As illustrated in the cross-section shown in broken section at **24**, the central-most portion **26** of the internal surface of the blank **20** is cylindrical with the outboard portions or facets **28** being angled relative thereto at angles typically in the range of from 1° to 30° relative to surface **26**. The axial extremes of the cross-section of this embodiment are generally semicircular, as illustrated at **32**, and the outer surface is configured to have cylindrical flats **34** and **36** on opposite sides of groove **22**, and angled facets or flats **38** and **40** on the opposite sides thereof. As an alternative, the facets **38** and **40** may be configured to have multiple facet surfaces.

Once removed from the mold, the blank **20** is shaped by machinery filing, sanding, trimming or other appropriate techniques and may be burnished as illustrated in FIG. 3 to provide a smooth or textured surface, and made ready for sintering: Once prepared, the blank **20** is inserted into a sintering oven and the temperature raised as suggested by the arrows **42**, to a suitable sintering temperature for a predetermined period of time during which the blank

becomes hardened and shrinks to a size appreciably smaller than the size of the original green blank. However, as indicated above, the mold was sized taking into consideration the anticipated subsequent shrinkage and as a result, the ring stock after sintering, has a predetermined size. This, of course, implies that a different mold will be required for each ring size. As an alternative, it will be understood that the blank may be pressed to have a tubular configuration from which multiple rings may be severed and machined to appropriate individual sizes.

Following the sintering operation, the ring stock can be ground and finish polished, and when appropriate, have a selected precious metal and/or other material installed in the groove **22** as suggested by the laying in of the soft metal strip **60** depicted in FIG. **5** of the drawings. Once the metal strip **50** is suitably installed using methods well known to jewelers, the assembly can be finish polished and made ready for market. It will, of course, be appreciated that other forms of materials can be inlaid into the groove **22**. For example, preformed metal, stone, ceramic, shell or other segments could be glued or otherwise affixed to the ring. Preferably, such items will be slightly recessed below the surfaces of the facets **34** and **36** so as to be protected thereby.

Turning now to FIG. **6**, which is a flow diagram illustrating the various steps followed in a preferred method of making a ring in accordance with the present invention. It will be noted that once a suitable press and mold has been prepared, the first step in making a ring or other object is to mix a predetermined combination of powdered metal of ceramic constituents to develop a sinterable metallic or ceramic powder. Once properly measured and disposed within the mold cavity, the powder will be compressed by the mold to develop an oversized "green" ring blank that, although somewhat fragile, is stable enough to allow certain processing to be accomplished prior to sintering. For example, mold lines may be trimmed and smoothed surfaces may be sanded or textured, facets may be smoothed etc. But once properly prepared, the next step is to load the blank at room temperature into a non-atmospheric sintering chamber and raise the temperature thereof to controlled temperatures, typically varying between 1000° C. to 2000° C. and then slowly cooled back to atmospheric temperature. Once cooled, the hardened ring stock or other blank configuration can be ground and polished to provide the hard metal or ceramic ring component. At this point, precious metal components, jewels and other decoration components may be affixed to the hard metal or ceramic part. One way to affix precious metal to the part is to use a brazing process and provide the components in varied shapes of wire sheet tubing or segments of other material that can be fabricated or forged into appropriate configurations and fit into the mating groove or channel **22**. Fluxed or flux free gold or silver soldered compounds varying in color and purity between 50% and 99% purity can be applied on or around desired mating surfaces of the hard material as well as the precious metal or other materials after mechanically binding the parts together with round or flat wire or heat resistant custom fixtures. Prepared fixtures with parts are then loaded at room temperature into a non-atmospheric chamber and heated to controlled temperatures varying between 1000° to 2000° C. and then allowed to cool down slowly to atmospheric temperature. This brazing operation will not interfere with the previously configured hard metal or ceramic components since their melting temperatures are substantially higher. A electron beam brazing process described elsewhere may alternatively be used.

Another method of mating the precious metal or other components to the hardened component is to engineer the hardened component with various features such as holes, notches, slots, etc., such that various pre-shaped precious metal or other materials in mating configurations may be snapped or pressed, swaged or burnished into the hardened substructure. The resulting mechanical fit will hold the components together.

Still another method of mating the precious metal or other components to the hardened component is to bond them to the hardened part by means of one or two part hardening resin compounds that are heat and room temperature cured.

Also precious metals can be directly cast into cavities in hard metal or ceramic articles using lost wax techniques widely used in jewelry making.

But notwithstanding the process used to mate the components together, once the several components are in fact combined, the entire assembly can be finished and polished to complete manufacture of the ring or other article of jewelry.

Turning now to FIGS. **7** through **14**, various cross-sectional configurations of rings are depicted illustrating combinations of flats, facets, materials, inserts and component relationships. More specifically, in FIG. **7**, a sintered metal part **60** is shown having a wide annular groove **62** formed in its outer surface and filled with a softer precious metal or other material **64**. The top surface of material **64** may be flush with the top edges **66** of the facets **68** or may be recessed there beneath to enhance the protective function of the hardened metal part **60**. This ring might have an axial length of 2–14 mm, wall thickness of 1–2.8 mm and have facets at angles of from about:Z% to 40% relative to the cylindrical surface **69**.

In FIG. **8**, a similar ring design is depicted, but in this case, utilizing a ceramic material as the hard surfaced part **70** with the sculpted precious metal part **72** being mounted within a groove **74** formed in the outer perimeter of the hard part **70**. Note the different surface effects that can be achieved by increasing the angular relationship of the various facets and by depressing or recessing the surface of the insert **72**.

FIGS. **8–10** depict two-groove embodiments of both sintered metal and ceramic substructures at **76** and **78** respectively, each having precious metal or other inserts **80** and **82** formed in the annular grooves thereof, with the exterior surfaces of the inserts of the rings being treated differently to achieve substantially different visual effects. Note, that in either case, the "hard part" protects the softer precious metal part. Note that in this embodiment, the internal surface **83** is shown aligned rather than faceted. Other embodiments may be treated likewise.

In FIG. **11**, a three-groove embodiment is depicted at **84**.

FIGS. **12–14** illustrate alternative embodiments in accordance with the present invention, wherein the hard metal or ceramic components are formed by two or more parts that are affixed together. For example, in FIG. **12**, complementary annular sintered or ceramic parts **86** and **88** are provided with shallow bores **90** at several points around facing surfaces of the components, and a plurality of annular components **92** made of at least two materials **92** are sandwiched together and bored at intervals matching the bores **90**, such that pins **94** may be extended through the bores in the ring components **92** with the ends thereof being extended into the bores **90** of the hardened ring components **86** and **88** to end mechanical stability to the assembly. The various components **92** would, of course, be epoxied or otherwise bonded together.

In FIGS. 13 and 14 three-part ring assemblies are illustrated at 96 and 98 respectively, with each being comprised of a central band 100 and 102 respectively, sandwiched between and mechanically bonded to a pair of exterior rings 104 and 105 respectively. In the case of the ring assembly illustrated in FIG. 13, for example, the exterior components 104 might be of sintered metal or of ceramic, while the interior band 100 might be of a precious metal, or even of a ceramic or sintered material. In the illustrated configuration, pockets 108 and azure holes 109 are formed in the interior band to receive gemstones 110 which are appropriately secured therein.

In the embodiment of FIG. 14, the interior band is depicted as being of a ceramic material sandwiched between and mechanically interlocked to exterior bands 106 made of sintered material or even precious metal, while the gemstones 112 are set in a precious metal 114.

FIG. 15 depicts at 120 a multifaceted unitary ring configuration made of a single, hard metal or ceramic substance. The six highly polished facets 121 on the outer surface of the ring create a unique design and visual impression heretofore not possible using prior art rings making techniques and technologies, because if such configuration had been made, the peaks 122 would have quickly been eroded, destroying the esthetic appearance of the ring.

In FIG. 16 of the drawing, still another alternative embodiment is depicted wherein a ring made primarily of precious metal 123 includes an annular insert 124 embedded therein and extending above the uppermost surface of the precious metal component to provide a protective and esthetically pleasing insert.

Alternatively, one or more holes or cavities may be provided around the ring for receiving precious metals and/or set stones.

The principal concept of this invention is the provision of an ultra durable hard metal or high tech ceramic type of jewelry that may or may not incorporate precious metals and/or precious gem stones. The invention also provides a unique jewelry manufacturing process that combines hard metals with precious metals in a manner such that the precious metals are flush or recessed slightly below the outer most surfaces of the hard metals over the outer wear surfaces to achieve maximum abrasion and corrosion resistance. This is not to preclude the use of protruding precious metal or gemstone components, but in such cases the protruding components would not be protected by the harder materials. The invention involves the provision of jewelry items made from super hard metals such as tungsten and cemented carbide and high tech ceramics of various colors processed into a predetermined shape then sintered in a furnace and ground and polished into finished form. These items may be shaped into concentric circular ring shapes of various sizes and profiles or individual parts may be ground into shapes that can be bonded to a precious metal substrate so as to protect the softer substrate. The hard metal circular designs encompass all types of profiles and cross-sectional configurations for rings, earrings and bracelets. Hard metal items may be processed with various sized and shaped openings distributed around the parameter, with other objects of precious metal gem stones or the like secured into the various openings for cosmetic purposes. Gem stones set in precious metal may be secured into said openings for protection from scratching and daily wear.

Another configuration similar to that depicted in FIG. 11 might include several concentric rings of varying widths and thickness of precious metal or other materials sandwiched between concentric ring's of varying widths, thicknesses

and profiles of hard metal. The components are assembled and bonded together with the softer precious metal surfaces being recessed below the adjacent surfaces of the hard metal, thereby causing all of the outer wear surfaces to be protected by the super hard metals surfaces.

Annular rings, earrings and bracelets may also be fashioned by combining variations of precious metal bands with the protective hard metal individual parts bonded onto and into slots or grooves or flat areas of the substrate precious metal bands. These hard metal parts will be positioned to give maximum protections to the precious metal parts.

Articles of jewelry may be created using symmetrical or asymmetrical grid-type patterns. Machined hard metal parts of varying shapes and sizes may be assembled and bonded onto or into a precious metal substrate designed where precious metal is recessed for maximum durability.

Articles of jewelry in accordance with the present invention may be made with various types of hard metals and precious metals where the hard metal is used for both esthetic and structural strength purposes. Hard metal rods of varying shapes and sizes maybe used in conjunction with precious metals to create a unique jewelry design having a very high structural strength. Articles of jewelry may be made entirely of hard metal or a combination of hard metal and precious metal where the cosmetic surfaces of the hard metal are ground to have a faceted look. These facets are unique to hard metal configurations in that precious metal is too soft and facet edges formed in such soft metals would wear off readily with normal everyday use.

The present invention has been described above as being comprised of a molded hard metal or ceramic component configured to protect a precious metal or other component; however, it will be appreciated that the invention is equally applicable to a multifaceted, highly polished jewelry item made solely of the hard metal composition or ceramic composition. Furthermore, the present invention relates to a method of making jewelry wherein a rough molded and sintered part is subsequently machined to produce multiple facets and surfaces that can be highly polished to provide an unusually shiny ring surface that is highly resistant to abrasion, wear and corrosion. As used in this description, the term facet is intended to include both cylindrical and frusto conical surfaces as well as planar or flat surfaces.

Having now described several embodiments of the invention, we now highlight a few exemplary embodiments of the invention.

In a first aspect, the invention provides an article, such as an item of jewelry, made of material selected from the group consisting of sintered metals and ceramics and having at least one highly polished facet formed on an outer surface thereof. In a second aspect, the invention provides an item of jewelry configured as an annular band having at least one annular groove formed in the outermost surface thereof and includes an insert of precious metal disposed within the groove. In a third aspect, the invention provides an item of jewelry wherein the outer surface of the inset of precious metal is recessed below adjacent extremities of the annular band. In a fourth aspect, the invention provides an item of jewelry wherein at least one gemstone is set in the insert of precious metal, the outermost surface of the gemstone being recessed beneath the adjacent extremities of the annular band. In a fifth aspect, the invention provides an item of jewelry wherein at least one gemstone is set in the insert of precious metal. In a sixth aspect, the invention provides an item of jewelry wherein at least one gemstone is set in a cavity in the band. In a seventh aspect, the invention provides an item of jewelry configured as an annular band

embedded in a concentric band of precious metal and having its outermost circumference protruding above the outermost circumference of the concentric band. In an eighth aspect, the invention provides an item of jewelry wherein the annular band is comprised of at least two components axially separated by and joined together by at least one annular band of precious metal. In a ninth aspect, the invention provides an item of jewelry wherein the axially separated annular bands are joined together by a plurality of concentric annular bands made of disparate materials. In a tenth aspect, the invention provides an item of jewelry wherein the annular band includes at least two grooves formed in the outer surface thereof, the two grooves being at least partially filled with a material other than that of the annular band.

In an eleventh aspect, the invention provides a method of providing an article, such as for example, an item of jewelry, where the method comprises the steps of: providing a pressure mold having a cavity of predetermined configuration formed therein; providing a mixture of two or more powdered materials that can be solidified upon the application of pressure and heat; depositing a predetermined quantity of the mixture of powdered materials within the cavity; compressing the quantity of powdered material to form a blank; and sintering the blank to form at least a component of the item of jewelry. This method may further be defined such that the item of jewelry is in the form of an annular band having a groove formed in the outer surface thereof, and further comprising the step of affixing a material within the outer groove, the outer surface thereof being recessed beneath the bounding edges of the groove. This method may be even further defined such that the affixed material is a precious metal that is affixed to the annular ring by brazing. The method may optionally be further defined such that the affixed material is affixed to the annular blank through the use of resinous materials. In a fifteenth aspect, the method may also include the step of finish polishing at least one surface of the annular blank. The method may be further defined such that the annular band has a plurality of facets formed in an outer surface thereof. In a seventeenth aspect, the invention may be further defined such that the affixed material is affixed to the annular blank by a mechanical interlocking of parts. In yet an eighteenth aspect, the inventive method may provide that the blank is severed to form a plurality of sub-blanks, each forming at least a component of the item of jewelry. In a nineteenth aspect, the method may further comprise affixing a gemstone or piece of precious metal to the item of jewelry. In another aspect, the method is further defined such that the component has a plurality of facets formed in an outer surface thereof.

While the certain embodiments of the article and method have been described with particular emphasis on jewelry items and articles, it is understood that neither the inventive article nor the apparatus or method for making the inventive article are limited to jewelry items but extends to all articles having the physical and materials properties described herein.

Alternative Embodiments

The invention also provides system, apparatus, and method or process for creating objects or articles, particularly composite articles, using wear-resistant or other materials, such as tungsten-carbide, poly or mono crystalline ceramics, and mixtures or alloys thereof. In one embodiment, the process is directed to the manufacture of articles having a circular, spherical, or cylindrical cross-section, such as items of jewelry or rings. In some embodiments, the

circular, spherical or cylindrical article will be combined with other shapes and/or deformed after fabrication so that the final article has a different shape than circular, spherical or cylindrical. The manufactured articles, particularly items of jewelry items, typically have inlays of a precious metal, such as gold, platinum, or alloys thereof. Characteristics and examples of some such articles and materials have been described elsewhere in the specification. However, it will be clear that the process described is not limited to the manufacture of items of jewelry, but may generally be applied to fabricating a variety of articles.

In a first embodiment of a process according to the present invention, a procedure is provided that permits the inlay of a metal having a lower melting point into one or more grooves or depressions in an underlying support or substrate. For example, the procedure is applicable to inlaying a precious or semi-precious metal such as gold into a groove in a sintered tungsten-carbide or ceramic ring. By lower melting point it is meant a metal (or alloy) having a temperature of fusion that is low relative to that of the material of the substrate.

An apparatus and process for manufacturing an article according to the present invention will now be described with reference to FIG. 17 through FIG. 20. FIG. 17 is a schematic side view of an embodiment of a vacuum deposition system 100 for forming an article 105 according to the present invention. FIG. 18 is a detailed view of an indexer 110 of the system 100 of FIG. 17. FIGS. 19A and 19B are schematic side views of an embodiment of a mandrel 115 for holding substrates 120. FIG. 20 is a flowchart of an embodiment of a process 125 for manufacturing an article 105 according to an embodiment of the present invention.

The process 125 involves rotating a substrate 120 of the article 105 being manufactured, such as a ring-shaped substrate, inside the vacuum deposition system 100 where a liquid cooled mandrel 115 covered by an electrically conductive sheath 135. In one embodiment, a number of substrates 120 are stacked along the mandrel 115 with thin washer shaped separators 140 to provide alternating substrate, separator, substrate, and the like. The electrical conductive sheath 135 can be made, for example, of extruded graphite or a metal-coated ceramic material such as aluminum oxide or mullite.

A spool 145 of metal wire 150 contained within the deposition system 100 is delivered via a delivery mechanism 160 through a nozzle 165 just behind a point or location 170 where an electron beam 175 (e-beam) is focused to strike the rotating substrate 120.

During an initial warm-up stage (Step 185) of the process 125 the electron beam 175 is deliberately de-focused (Step 190) to preheat (Step 195) the substrate 120. Typically the substrate 120 is preheated to a temperature of between about 300 to about 600° F. (150 to 300° C.).

After preheating, the electron beam 175 is finely focused (Step 200) at a focal point 205 coincident with the width of a grooved portion 210 having a recessed groove 215 or depression on a surface of the substrate 120. Simultaneously, the metal wire 150 is fed through the nozzle 165 into the path of the focused electron beam 175, and as a result of the impact of the electrons from the electron beam, heated causing it to virtually instantaneously liquefy (Step 225) and flow into the groove 215 of the substrate 120. Wire 150 is continuously fed and heated until an adequate amount of metal has been deposited or applied to the groove (Step 230). The energy in electron beam 175 is then gradually reduced (Step 235) to allow solidification of the metal in the groove 215 and cooling of the article 105.

The mandrel **115** is then stepped or indexed (Step **245**) using the indexer **110** shown in FIG. **18** to a center of the grooved portion **210** of the next substrate **120**, and the process **125** repeated (Steps **185** to **245**) until all substrates have been metalized, that is until all substrates have had metal deposited into the groove **215**.

Preferably, a temperature sensor **255**, such as an optical pyrometer, is provided within vacuum deposition system **100** to read the temperature of the substrate **120** and to provide the temperature to a control program (not shown) that precisely controls the delivery mechanism **160**, indexing of the indexer **110** and the power and focus of the electron beam **175** to produce an article **105** having a uniform and seamless band of metal about the substrate **120**. Alternatively, if the degree of uniformity is not critical, a simple open loop control (not shown) in which the metal wire **150** is fed at a constant rate, the indexer **110** indexed, and the electron beam **175** is powered up and focused at regular intervals, can be provided rather than the feedback control using temperature, but is not preferred.

Because a sensing lens **265** or window of the temperature sensor **255** is susceptible to metal deposition resulting from vaporization of some of the molten metal in the vacuum deposition system, a lens shield **270** may advantageously be interposed between the sensing lens **265** and the substrate **120**. The shield **270** can be made from Mylar or other clear (optically transparent) material placed in between the sensing lens **265** and the substrate **120**. Preferably, the lens shield **270** is a thin strip or tape of material which is continuously moved past sensing lens **265** of the temperature sensor **255** during the metalization process **125**, thus allowing the temperature sensor to always read the temperature accurately. Alternatively or in addition thereto, the sensor lens **265** may be covered by a shutter or other movable cover **275** so that the sensor lens is covered at all times while liquid or gaseous metal is present in the system **100**. The cover **275** is moved away from the sensor lens **265** during the preheating phase (step **195**) to ensure that preheat temperature is reached before the metalization step begins.

As already described, this first process **125** for depositing a layer of material having a lower melting point than the substrate **120** can only be used with certain materials. When the melting temperature of the inlay material is higher than the substrate **120**, heating the substrate and/or depositing the molten metal may, at the very least, damage or deform the substrate. Hence, an alternative second process **285** has been developed for inlaying materials having a high melting temperature, such as platinum, or alloys thereof, onto a substrate **120**. Such high temperature materials cannot be directly melted into the groove **215** by the first process **125** described above because their melting temperature is as high or higher than the sintering temperature or temperature of fusion of the substrate. This second process **285** can also be used where the melting temperature of the inlay material is below the melting or sintering temperature of the substrate **120**.

The second process **285** involves the fabrication of the article **105** using swaging and braising operations. Generally, the metal wire **150** is soldered or welded to form a joint-less metal ring **290** (or otherwise fabricating or machining to form a seamless metal ring or other article) that is then squeezed or swaged onto a sintered substrate **120**. A braising material (not shown) having a melting point lower than both the metal ring **290** and the substrate **120** is applied to a junction (not shown) between the metal ring and the substrate to wick into the junction by capillary action,

thereby forming a solid unitary article **105** having substantially no gaps or interstitial recesses between the metal ring and the substrate.

FIG. **21** shows a schematic diagram of an exemplary embodiment of a mechanical press **300** suitable for swaging or squeezing the metal ring **290** onto the substrate **120** according to the second process **285** of the present invention. The press **300** generally includes several rods or mandrels **305** to hold the substrate **120** with the metal ring **290** disposed thereabout, one or more threaded, tapered top collets **310** into which the mandrel is placed, one or more collet-blocks **315** having tapered openings **320** into which the collet is forced to squeeze or swage the metal ring to the substrate a pneumatic or hydraulic power cylinder **325** to force the collet into the opening in the collet block. In operation, air or hydraulic fluid from a pressurized supply **335** is admitted to the power cylinder **325** through a manual or electronic valve **340**. In the embodiment shown in FIG. **21** the press **300** further includes a hydraulic fluid cylinder **345** to which air is applied and a pneumatic multiplier **350** to convert the relatively low pressure air to a higher hydraulic fluid pressure. Pneumatic multipliers **350** typically raise the pressure of a hydraulic fluid to a pressure from 4 to 12 times that of the pneumatic air. For example, supplying 50 pounds per square inch (psi) of air can produce 600 psi in a hydraulic fluid supplied to the collet-blocks **315**.

Preferably the mandrel **305**, shown in detail in FIG. **22**, has an outer diameter (OD) sized to re-enforce or support the substrate **120** during the manufacturing process **285**. More preferably, the mandrel **305** is of an expanding type that has an OD that can be adjusted to be substantially the same as the inner diameter (ID) of the substrate **120** to apply a counter-force directed radially outward from the substrate thereby preventing it from deforming or cracking when force is applied to the OD of the substrate.

The top collets **310** have a generally hollow cylindrical shape and are threaded at one end to engage a threaded fitting inside the opening **320** in the collet-blocks **315**. The collets **310** are tapered from an OD larger than the metal ring **290** to a minimum OD near the threaded end, and are segmented axially to form three or more arcuate prongs or tines **355** that are deformed radially inward as the top collet is pulled into the opening **320** in the collet-block **315**. The collet-block **315** also tapers from an ID slightly larger than the OD of the metal ring **290** to a minimum ID slightly smaller than the OD of the substrate **120**. As the top collet **310**, with the mandrel **305** positioned therein, is pulled into the opening **320** in the collet-block **315**, the arcuate tines **355** of the collet move radially inward to swage the metal ring **290** to the substrate **120**. This can be accomplished either by pulling the top collet **310** down through the opening **320** in the collet-block **315** or by raising the collet-block over the top collet.

A process for manufacturing an article **105** according to the present invention will now be described with reference to FIG. **23**. FIG. **23** is a flowchart of steps for manufacturing the article according to the second process **285**.

In an initial step, (step **365**) ends of a metal wire are joined and soldered to form a joint-less metal ring **290** having an ID larger than an OD of the substrate **120**. The metal ring **290** is placed over the groove **215** in the substrate **120**. (step **370**). The substrate **120**, with the metal ring **290** assembled thereon, is then placed on the mandrel **305**. (step **375**). Optionally, if the mandrel **305** is of the expanding type, the OD of the mandrel adjusted to be substantially the same as the ID of the substrate **120**. (step **378**) The mandrel **305**, with the metal ring **290** and substrate **120** assembly thereon is

positioned in the top collet **310** in the collet-block **315**. (step **380**). The pressure supply valve **340** is opened admitting pressurized air or hydraulic fluid to the power cylinder **325** forcing the top collet **310** through the opening **320** in the collet-block **315** and swaging the metal ring **290** to the substrate **120**. (step **385**). The pressure supply valve **340** is closed and the mandrel **305** removed. (step **390**) In a preferred embodiment, the process **285** is a multi-step process in which the top collet **310** with the mandrel **305** therein is moved through a sequence of collet-blocks **315** having successively smaller minimum ids so as to yield a snug fit of the metal ring **290** onto the substrate **120**. For example, in the embodiment of the mechanical press **300** shown in FIG. **21**, the process can be a three step process in which the three collet-blocks **315** shown have openings **320** that are large, medium or small relative to one another.

After the metal ring **290** is swaged to the substrate, the assembly is removed from the mandrel **305**, optionally but desirably checked for cracks and then cleaned (step **395**) prior to beginning the braising process.

A preferred braising process (step **400**) uses an electron beam **175** similar to that described above in the first process **125** but substituting silver, gold or a eutectic alloy wire **150** as a braising material to bond the metal ring **290** and the substrate **120** together rather than to fill the groove **215**.

In an alternative braising step (not shown), the braising can be accomplished by applying a braising material near the groove **215** in the assembled metal ring **290** and substrate **120** and heating the assembly in a vacuum chamber or other oxygen free environment. The assembly is slowly raised to the proper temperature and then slowly cooled to complete the braising operation. In yet another alternative braising step (not shown), the braising can be accomplished by depositing a thin strip or small amount of braising material in the groove **215** prior to the swaging operation and then heating the assembly as described above.

After the metalizing process (steps **365** to **400**) is completed, the article **105** is mounted into a fixture (not shown) in a lathe (not shown) and the excess metal removed. (step **405**).

Although described relative to a process for flowing molten precious or semiprecious metal into a groove **215** in a ring-shaped substrate **120**, the inventive process **125** is not so restricted. It may, for example, be utilized for any application in which it is desired to deposit one metal material onto a substrate, independent of the form or composition of the substrate. Examples of such alternative applications include: medical devices and implants, dental devices and implants, industrial and electronic devices and components, and so forth.

It is to be understood that even though numerous characteristics and advantages of certain embodiments of the present invention have been set forth in the foregoing description, together with details of the structure and function of various embodiments of the invention, this disclosure is illustrative only, and changes may be made in detail, especially in matters of structure and arrangement of parts within the principles of the present invention to the full extent indicated by the broad general meaning of the terms in which the appended claims are expressed.

What is claimed is:

1. A method of making a jewelry article which comprises: providing an annular substrate formed of a hard material predominantly comprising tungsten carbide and having an outer surface with an outer diameter and a depression disposed circumferentially in its outer surface;

providing a metal band having an inner diameter that is greater than the outer diameter of the annular substrate; and

inwardly deforming the metal band to squeeze it into the depression in the outer surface of the annular substrate so as to form the jewelry article, wherein the hard material is sufficiently hard to avoid being deformed during the inward deforming of the metal band.

2. The method of claim **1**, which further comprises lathing excess material to remove it from the depression.

3. The method of claim **1**, wherein the depression extends entirely around the annular band.

4. The method of claim **1**, wherein the metal band is selected to comprise a precious metal or an alloy thereof, a gemstone, or a combination thereof.

5. The method of claim **1**, which further comprises affixing a decorative component comprising at least one of a precious metal, stone, gemstone, crystal, or a combination thereof, to the jewelry article.

6. The method of claim **1**, which further comprises providing the jewelry article with a metal article attached or integrally formed therewith to facilitate attachment of a stone, gemstone, crystal, or a combination thereof.

7. The method of claim **1**, which further comprises forming a plurality of facets in the outer surface of the tungsten carbide substrate material.

8. The method of claim **1**, wherein the jewelry article is a ring configured and adapted to receive a wearer's body part through an aperture in the ring.

9. The method of claim **1**, wherein the annular substrate is formed as a unitary band.

10. The method of claim **1**, wherein the hard material is formed by sintering powders that consist essentially of tungsten carbide and a metal binder material.

11. The method of claim **1**, wherein providing the metal band comprises providing a metal insert having first and second ends and inwardly deforming the metal band comprises joining the first and second ends thereof so that the metal band is at least partially disposed in the depression on the outer surface of the annular substrate.

12. The method of claim **11**, further comprising joining a first end and a second end of the elongated metal insert to each other after the metal insert is disposed at least partially in the depression.

13. The method of claim **12**, wherein the joining comprises soldering the first and second ends together.

14. The method of claim **1**, wherein the elongated metal insert is disposed entirely in the depression so that an outermost portion thereof is no larger than the outer diameter of the annular ring to form the jewelry article.

15. A method of making a jewelry article which comprises:

providing an annular substrate formed of a hard material comprising tungsten carbide and having an outer surface with an outer diameter and a depression disposed circumferentially in its outer surface;

providing a metal band having an inner diameter that is greater than the outer diameter of the annular substrate; and

inwardly deforming the metal band to squeeze it into the depression in the outer surface of the annular substrate so as to form the jewelry article which further comprises heating the metal band or brazing the metal band using a brazing material, or both, to assist in attaching the metal band to the annular substrate.

16. The method of claim **15**, wherein the annular substrate and the metal band comprise fusible material, and wherein

17

the brazing comprises heating the brazing material to a temperature greater than a temperature of fusion thereof and below temperatures of fusion of the annular substrate and the metal band.

17. The method of claim 15, wherein a portion of the brazing material is disposed in a portion of the depression before the metal band is inwardly deformed into the depression and then sufficiently liquefied therein to facilitate permanently joining the metal band and the annular substrate.

18. The method of claim 15, wherein the brazing material comprises a precious metal or an alloy thereof.

19. A method of making a jewelry article which comprises:

providing an annular substrate formed of a hard material comprising tungsten carbide and having an outer surface with an outer diameter and a depression disposed circumferentially in its outer surface;

providing a metal band having an inner diameter that is greater than the outer diameter of the annular substrate;

heating the metal band or brazing the metal band using a brazing wire, or both, to assist in attaching the metal band to the annular substrate;

contacting the brazing wire proximate a point of contact between the annular substrate and the metal band;

heating the brazing wire sufficiently so that it liquefies and flows into the junction; and

continuously feeding the brazing wire into the depression while heating and moving the point of contact to cause the liquified wire to at least substantially fill interstitial gaps between the annular substrate and the metal band; and

18

inwardly deforming the metal band to squeeze it into the depression in the outer surface of the annular substrate so as to form the jewelry article.

20. The method of claim 19 wherein the heating includes directing an electron beam onto the brazing wire.

21. The method of claim 19 which further comprises adding a further material into the depression to assist in bonding the metal band to the substrate.

22. The method of claim 21 which further comprises providing at least a portion of the further material in the depression prior to heating.

23. The method of claim 21 which further comprises preheating the further material or metal band to assist in bonding the metal band to the substrate.

24. A method of making a jewelry article which comprises:

providing an annular substrate formed of a hard material comprising tungsten carbide and having an outer surface with an outer diameter and a depression which comprises one or more apertures in the annular band and which depression is disposed circumferentially in its outer surface;

providing a metal band having an inner diameter that is greater than the outer diameter of the annular substrate; and

inwardly deforming the metal band to squeeze it into the depression in the outer surface of the annular substrate so as to form the jewelry article.

* * * * *